

# VT-441

## Laminate/Prepreg

UL Approval: E214381    Version: C1 /127 /128

### General Information

- > Phenolic Cured System
- > Halogen Free & Mid-Tg FR4.1
- > UV Blocking
- > CAF Resistance
- > Low Z-CTE
- > Excellent Thermal Reliability



### Application

Mobile Phone, Smart Phone, Computer, Instrumentation, Communication Equipment, Electronic Game Machine, VCR, etc.

### Availability

- > Core Thickness: 0.002" (0.05mm) to 0.200" (5mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 1500, 2113, 2313, 3313, 2116, 1080, 1086, 1078, 106 &1067, etc.

Note: For cores  $\leq 0.005"$ , it is recommended to use the reverse treated copper due to the low profile. The peel strength for RT foil is  $\approx 1-2\text{lbs/in}$  (0.35Kg/m) less than standard foil.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

#### CORPORATE HEADQUARTERS

**Ventec Electronics Co. Ltd.**  
308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129  
T: +86 512-68091810  
Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

**Ventec Europe**  
Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK  
T: +44 1926-889822  
Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

**Ventec USA**  
720 Lee St., Elk Grove Village,  
Illinois, IL 60007,  
United States of America  
T: +1 630-4221627  
Email: saleseast@ventec-usa.com

[www.ventec laminates.com](http://www.ventec laminates.com)

# VT-441

## Laminate/Prepreg

UL Approval: E214381 Version: C1 /127 /128

### Properties Sheet IPC-4101E /127 /128

Properties	Test Method	Units	Specification	Typical Value	
<b>Thermal Properties</b>					
Tg	DSC	IPC-TM-650 2.4.25	°C	150 minimum	152
	TMA	IPC-TM-650 2.4.24	°C	150 minimum	158
Td		ASTM D3850	°C	325 minimum	385
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288		IPC-TM-650 2.4.24.1	Minute	5 minimum	>30
Thermal Stress @ 288 °C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum	38
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum	190
	Total Expansion (50~260 °C)	IPC-TM-650 2.4.24	%	3.5 maximum	2.2
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	-	11~13
MOT		UL 94	°C	-	130
<b>Electrical Properties</b>					
DK @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	-	5.4 maximum	4.4
DF @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	-	0.035 maximum	0.014
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	-	Grade 3 (175~250)
Arc Resistance		ASTM D495	Second	-	187
<b>Mechanical Properties</b>					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	-	7.9~10 (1.2~1.6)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	7.9~10 (1.2~1.6)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	72 (500)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	58 (400)
<b>Physical Properties</b>					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.18
Flammability		UL-94	Rating	V-0 minimum	V-0

Note: All test data provided are typical values and are not intended to be specification values.

Disclaimer: The information and data contained in this technical literature is based on data and knowledge correct at the time of publishing/printing and is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own

#### CORPORATE HEADQUARTERS

##### Ventec Electronics Co. Ltd.

308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

##### Ventec Europe

Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

##### Ventec USA

720 Lee St., Elk Grove Village,  
Illinois, IL 60007,  
United States of America

T: +1 630-4221627

Email: saleseast@ventec-usa.com

www.ventec laminates.com