


# T-P INS 0.25 AO/A1 – ELECTRICALLY INSULATING

## DATASHEET



### FEATURES

- High tensile strength, designed to prevent cut through and electrical shorts
- Low Thermal Impedance
- UL94-V0 recognised
- No viscosity, 0.25mm thick
- Adhesive option available (A1)

### APPLICATIONS

- SMPS, Telecom Devices, Visual Devices, Networking Products, LCD-TV, Notebook PC's, PC's, ME, Household Applications etc.

PROPERTIES	TEST METHOD	UNIT	T-P-INS AO
Material	-	-	Thermally Conductive Silicon Cloth
Colour	Visual	-	Grey
Thickness (±10%)	-	-	0.25
Thermal Conductivity	ASTM-D5470	W/mK	0.8
Hardness (+/- 5%)	ASTM-D2240	Shore C	70
Flammability Rating	UL94	-	V0
Breakdown Voltage (1.0mm)	ASTM-D149	kV	≥6
Specific Gravity	-	g/cm <sup>3</sup>	1.7
Working Temperature	-	°C	-40 - 200
Volume Resistance	ASTM-D257	Ohm-cm	10 <sup>15</sup>

### THERMAL IMPEDANCE (0.25MM)

	5	10	15	20	25	30
Pressure (psi)	5	10	15	20	25	30
Thickness (mm)	0.25	0.25	0.24	0.24	0.24	0.24
Compression Ration (%)	3.8	3.8	3.7	3.7	3.7	3.7
Thermal Impedance (C-in <sup>2</sup> /W)	1.01	0.97	0.91	0.87	0.84	0.82

### NOTES

- Customised shapes are available
- The above performance data is tested in an environment of 70% humidity, temperature 25 °C
- This data is intended for reference purposes only. It is recommended that the material is tested to fully evaluate its performance ensuring it is fit for purpose.

Publish date : 08/12/20

#### Ventec International Group

##### United Kingdom

Unit 1 Trojan Business Centre, Tachbrook  
 Park Estate Leamington Spa, CV34 6RH  
 Tel: +44 1926-889822

##### Germany

Morschheimerstrasse 15  
 67292 Kirchheimbolanden  
 Tel: +49 6352-753260

EMI Thermal is a brand of DK-Daleba

emithermal@ventec-europe.com  
 www.venteclaminates.com