



ThinFlex



ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C. (Kaohsiung Science Park) Tel: +886-7-6955236 Fax: +886-7-6955539 http://www.thinflex.com.tw e-mail: service@thinflex.com.tw

# ThinFlex-A, A-1020ED Adhesiveless Double Sided Copper Clad Laminate (Halogen Free)

ThinFlex-A, A-1020ED is an adhesiveless double-sided (D/S) copper clad laminate, using UBE TPI film and laminated with ED copper foil on both sides. ThinFlex-A, A-1020ED adhesiveless D/S composites are designed for a wide variety of flexible circuit applications which require advanced material performance, temperature resistance, fine pitch, and high reliability.

## 1. Product Characteristics:

- \* Excellent dimensional stability
- \* Excellent flexibility
- \* Finer line etching capability
- \* Low moisture absorption
- \* Excellent flammability (Flame class UL 94 V-0; UL File No. E219724)
- \* Excellent chemical resistance
- \* Excellent thermal, mechanical, and electrical properties

## 2. Specifications:

A - 10 20 E D

Product	Thickness of PI	Thickness of Cu	Cu Type	Structure
A-type FCCL	10 : 1.0 mil	20 : 2.0 oz	E : ED	Double-sided
Supply Size	W: 250/500 ± 1mm; L: 400~700 ± 2mm (sheet type) W: 250/500 ± 1mm; L: 100 +2/-0m (roll type)			

**\*Other thicknesses and dimensions are available on customers' demand.**



ThinFlex

Distributed by:  
**ventec**  
INTERNATIONAL GROUP  
騰輝電子

**ThinFlex Corporation**

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.  
(Kaohsiung Science Park)  
Tel: +886-7-6955236 Fax: +886-7-6955539  
<http://www.thinflex.com.tw>  
e-mail: service@thinflex.com.tw

### 3. Construction:

Copper foil
Polyimide film
Copper foil

### 4. Properties:

Test item	Unit	A-1020ED	Test Method	
Peel Strength				
As Received	Kgf/cm	≥ 1.2	IPC-TM650 2.4.9	
Solder Float	Kgf/cm	≥ 1.2	IPC-TM650 2.4.9	
After Temp. Cycling	Kgf/cm	≥ 1.2	IPC-TM650 2.4.9	
Chemical Resistance	Kgf/cm	≥ 1.2	IPC-TM650 2.3.2	
Tensile Strength (Base Film)	Kg/mm <sup>2</sup>	≥ 28	IPC-TM-650 2.4.19	
Elongation (Base Film)	%	≥ 50	IPC-TM-650 2.4.19	
Tensile Modulus (Base Film)	Kg/mm <sup>2</sup>	≥ 550	ASTM D882	
Initial Tear Strength (Base Film)	g	≥ 800	IPC-TM-650 2.4.16	
Propagation Tear Strength (Base Film)	g	≥ 10	IPC-TM-650 2.4.17.1	
Flexural Endurance, MIT				
M.D.	Cycles	≥ 50	JIS-C 6471, 0.8mmR, 0.5kg	
T.D.	Cycles	≥ 50	JIS-C 6471, 0.8mmR, 0.5kg	
Electrical Properties				
Surface Resistance	Ω	~10 <sup>11</sup>	IPC-TM650 2.5.17	
Volume Resistance	Ω-cm	~10 <sup>12</sup>	IPC-TM650 2.5.17	
Insulation Resistance	Ω	~10 <sup>9</sup>	IPC-TM650 2.6.3.2	
Dielectric Strength	kV/mil	6.9	ASTM-D149	
Dielectric Constant	-	3.3	IPC-TM650 2.5.5.3	
Dissipation factor	-	0.002	IPC-TM650 2.5.5.3	
Physical and Thermal Properties				
Dimensional Stability	M.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
	T.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
CTE		ppm/°C	19.3	ThinFlex
T <sub>g</sub>		°C	350	ThinFlex
Solder Float	10sec at 288°C (550°F)	-	Pass	IPC-TM650 2.4.13
Moisture Absorption Test		%	1.1	IPC-TM650 2.6.2
Chemical Resistance-single		-	Pass	IPC-TM650 2.3.2
Thickness tolerance		um	165±10%	ThinFlex
UL Flame Class		-	V-0	UL94

\* Above data are typical values, and are not guaranteed values.



ThinFlex

Distributed by:  
**ventec**  
INTERNATIONAL GROUP  
騰輝電子

**ThinFlex Corporation**

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.  
(Kaohsiung Science Park)  
Tel: +886-7-6955236 Fax: +886-7-6955539  
<http://www.thinflex.com.tw>  
e-mail: [service@thinflex.com.tw](mailto:service@thinflex.com.tw)

## 5. Storage:

ThinFlex-A, A-1020ED will meet its shelf-life for at least 12 months after arrival at the user's factory when stored in the original packaging at temperatures of below 30°C and below 70% humidity. The products do not need refrigeration and should not be frozen.

Note: The information and data contained in this technical literature is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.

## ThinFlex Corporation

No.8, Luke 2<sup>nd</sup> Rd., Luzhu Dist., Kaohsiung City 821, Taiwan, R.O.C. (Kaohsiung Science Park)  
Tel: +886-7-6955236 Fax: +886-7-6955539  
<http://www.thinflex.com.tw>  
e-mail: [service@thinflex.com.tw](mailto:service@thinflex.com.tw)