

pro-bond 4C - VT-464LT RCC

UL Approval: E214381 Version: 23/03/2024

Low Dk/ Low Df Resin Coated Copper Bondply

Resin Coated Copper (RCC) Bondply is an unreinforced adhesive system coated onto ultra-thin copper foil (1.5-5.0µm supported on an 18µm carrier foil) for use in high performance and high reliability multilayer PCB stack-ups.

VT-464LT is a high Tg, ceramic-filled, low Dk (3.05) & low Df (0.0065), halogen-free thermoset resin system, specifically designed for use in multilayer PCBs with Ventec **tec**-speed laminates & prepregs, and it is also fully compatible with other resin systems in hybrid stack-ups.

General Information

- > Halogen free, Dk 3.05 & Df 0.0065
- > Ultra-thin dielectric layer
- > Suitable for sequential laminations
- > Unreinforced adhesive for better electrical isotropic consistency
- > Excellent flow characteristics and filling ability, designed for fine line and space
- > Laser drillable
- > Excellent laser hole pattern consistency

Application

- > Interposers
- > Probe Cards
- > Anti-shake Coils
- > Packaging Modules

Availability

Press Ply Thickness	25µ/50µ (0.0010"/0.0020")
Copper Foil Thickness	(18µm Carrier Foil) 1.5µm/2.0µm/3.0µm/5.0µm
Panel Size	610mmx457mm (24"x18")

Part Numbers

Description	Part Number
pro-bond 4C RCC Cu 1.5µm Die 25µm	464LT-C15-025
pro-bond 4C RCC Cu 1.5µm Die 50µm	464LT-C15-050
pro-bond 4C RCC Cu 2.0µm Die 25µm	464LT-C20-025
pro-bond 4C RCC Cu 2.0µm Die 50µm	464LT-C20-050
pro-bond 4C RCC Cu 3.0µm Die 25µm	464LT-C30-025
pro-bond 4C RCC Cu 3.0µm Die 50µm	464LT-C30-050
pro-bond 4C RCC Cu 5.0µm Die 25µm	464LT-C50-025
pro-bond 4C RCC Cu 5.0µm Die 50µm	464LT-C50-050

pro-bond 4C - VT-464LT RCC

UL Approval: E214381 Version: 23/03/2024

Low Dk/ Low Df Resin Coated Copper Bondply

Properties

Properties		Test Method	Units	Typical Value
Electrical Properties				
Dk (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.13	-	3.50
	@ 10GHz			3.05
Df	@ 1GHz	IPC-TM-650 2.5.5.13	-	0.0050
	@ 10GHz			0.0065
Thermal Properties				
Tg	DMA	IPC-TM-650 2.4.24.4	°C	295
Td	TGA	ASTM D3850	°C	380
CTE	α_1 (<Tg)	IPC-TM-650 2.4.24	ppm/°C	15.5
	α_2 (>Tg)		ppm/°C	45
Thermal Stress	@ 288°C (10s/Cycle)	IPC-TM-650 2.4.13.1	Second	>300
Thermal Conductivity		ASTM D5470	W/mK	0.5
Mechanical Properties				
Peel Strength - 5µm (Plated to 20µm)		IPC-TM-650 2.4.8	N/mm (lb/in)	0.65 (3.7)
Tensile Modulus	40°C	IPC-TM-650 2.4.24.4	GPa	9.2
Physical Properties				
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.08
Flammability (in Lab)		UL 94	Rating	V-0

All test data provided are typical values and not intended to be specification values.

Storage Condition

		RCC	
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)
	Relative Humidity	Below 55% RH	/

Disclaimer:

- > The information and data contained in this technical literature is based on data and knowledge correct at the time of publishing/printing and is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.