

VT-441

UL Approval: E214381 Version: B5 /127 /128

Laminate/Prepreg

General Information

- > Phenolic Cured System
- > Halogen Free & Mid-Tg FR4.1
- > UV Blocking
- > CAF Resistance
- > Low Z-CTE
- > Excellent Thermal Reliability

Application

Mobile Phone, Smart Phone, Computer, Instrumentation, Communication Equipment, Electronic Game Machine, VCR, etc.

Availability

- > Core Thickness: 0.002" (0.05mm) to 0.200" (5mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 1500, 2113, 2313, 3313, 2116, 1080, 1086, 1078, 106 &1067, etc.

Note: For cores $\leq 0.005"$, it is recommended to use the reverse treated copper due to the low profile. The peel strength for RT foil is $\approx 1-2\text{lbs/in}$ (0.35Kg/m) less than standard foil.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America
T: +1 978-5219700
Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-441

Laminate/Prepreg

UL Approval: E214381 Version: B5 /127 /128

Properties Sheet IPC-4101E /127 /128

Properties	Test Method	Units	Specification	Typical Value	
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	-	152
	TMA	IPC-TM-650 2.4.24	°C	145 minimum	158
Td		ASTM D3850	°C	325 minimum	385
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288		IPC-TM-650 2.4.24.1	Minute	5 minimum	>30
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum	38
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum	190
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	3.5 maximum	2.2
MOT		UL 94	°C	-	130
Electrical Properties					
DK @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	-	5.4 maximum	4.4
DF @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	-	0.035 minimum	0.014
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	-	Grade 3 (175~250)
Arc Resistance		ASTM D495	Second	-	187
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	-	7.9~10 (1.2~1.6)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	7.9~10 (1.2~1.6)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	72 (500)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	58 (400)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.18
Flammability		UL-94	Rating	V0 minimum	V0

Note: All test data provided are typical values and are not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
 308 TaiShan Rd,
 New District Suzhou,
 Jiangsu, P.R. China 215129
 T: +86 512-68091810
 Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
 Unit 1 Trojan Business Centre,
 Tachbrook Park Estate,
 Leamington-Spa, CV34 6RH, UK
 T: +44 1926-889822
 Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
 21 Water Street, Amesbury,
 Massachusetts, MA 01913,
 United States of America
 T: +1 978-5219700
 Email: saleseast@ventec-usa.com

www.ventec laminates.com