

VT-42A

Laminate/Prepreg

UL Approval: E214381 Version: A2 /21

General Information

- > Dicy Cured System
- > Standard FR4.0 (Tg135°C)
- > UV Blocking

Application

Computer, Communication Equipment, TV, VCR, Electronic Game Machine, etc

Availability

Available Products List

Thickness Overall (mm)	Class L Tolerance (mil)	Thickness Core (mil)
1.0mm 1/1	+/- 3.9	36
1.0mm H/H	+/- 3.9	36
1.2mm 1/1	+/- 5.1	45
1.2mm H/H	+/- 5.1	45
1.5mm 1/1	+/- 5.1	57
1.5mm H/H	+/- 5.1	58
1.5mm 1/0	+/- 5.1	58

- Not for use in critical anti-CAF applications.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
 308 TaiShan Rd,
 New District Suzhou,
 Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
 Unit 1 Trojan Business Centre,
 Tachbrook Park Estate,
 Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
 21 Water Street, Amesbury,
 Massachusetts, MA 01913,
 United States of America
T: +1 978-5219700
Email: saleseast@ventec-usa.com

www.ventecclaminates.com

VT-42A

Laminate/Prepreg

UL Approval: E214381 Version: A2 /21

Properties Sheet IPC-4101E /21

Properties		Test Method	Units	Specification	Typical Value
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	110 minimum	135
Td		ASTM D3850	°C	–	310
T260		IPC-TM-650 2.4.24.1	Minute	–	20
T288		IPC-TM-650 2.4.24.1	Minute	–	2
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	300
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	–	50
	After Tg	IPC-TM-650 2.4.24	ppm/°C	–	250
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	–	3.75
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	–	12~14
MOT		UL 94	°C	–	130
Electrical Properties					
DK @ 1GHz		IPC-TM-650 2.5.5.9	–	5.4 maximum	4.2
DF @ 1GHz		IPC-TM-650 2.5.5.9	–	0.035 maximum	0.015
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 3 (175~250)
Arc Resistance		IPC-TM-650 2.5.1	Second	60 minimum	240
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	10~12 (1.7~2.0)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	9~12 (1.5~2.0)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	87 (600)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	72 (500)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.25
Flammability		UL-94	Rating	V0 minimum	V0

- 1) All test data provided are typical values and not intended to be specification values.
- 2) Standard VT-42A products can not meet Anti-CAF requirement.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
 308 TaiShan Rd,
 New District Suzhou,
 Jiangsu, P.R. China 215129
 T: +86 512-68091810
 Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
 Unit 1 Trojan Business Centre,
 Tachbrook Park Estate,
 Leamington-Spa, CV34 6RH, UK
 T: +44 1926-889822
 Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
 21 Water Street, Amesbury,
 Massachusetts, MA 01913,
 United States of America
 T: +1 978-5219700
 Email: saleseast@ventec-usa.com

www.ventecclaminates.com