

tec-speed 2.1 - VT-461

UL Approval: E214381 Version: B3 /97 /98 /99 /101 /126

Laminate/Prepreg

General Information

- > Mid Dk & Mid Loss
- > FR4.0
- > Excellent Thermal Reliability
- > Lead Free Process Compatible
- > High Tg
- > Ease of Manufacturing

Application

Server, Router, Satellite Communication, Storage, Backpanel, Navigation, etc

Availability

- > Core Thickness: 0.002" (0.05mm) to 0.200" (5mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 1500, 2113, 2313, 3313, 2116, 1080, 1086, 1078, 106 & 1067, etc
- > Ability of Processing Copper Type: HTE, RTF, VLP & HVLP

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America
T: +1 978-5219700
Email: saleseast@ventec-usa.com

www.ventecclaminates.com

tec-speed 2.1 - VT-461

UL Approval: E214381 Version: B3 /97 /98 /99 /101 /126

Laminate/Prepreg

Properties Sheet IPC-4101E /97 /98 /99 /101 /126

Properties		Test Method	Units	Specification	Typical Value
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	170 minimum	175
	TMA	IPC-TM-650 2.4.24	°C	–	–
Td		ASTM D3850	°C	340 minimum	370
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288		IPC-TM-650 2.4.24.1	Minute	15 minimum	>30
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum	40
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum	240
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	3.0 maximum	2.8
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	–	11~13
MOT		UL 94	°C	–	130
Electrical Properties					
DK (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	–	5.2 maximum	3.9
	@ 10GHz	IPC-TM-650 2.5.5.13	–	–	3.8
DF (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	–	0.035 maximum	0.0080
	@ 10GHz	IPC-TM-650 2.5.5.13	–	–	0.0095
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1372 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 3 (175~250)
Arc Resistance		ASTM D495	Second	60 minimum	195
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	8.0 (1.40)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	8.0 (1.40)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	80 (560)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	65 (450)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.12
Flammability		UL-94	Rating	V0	V0

All test data provided are typical values and not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America
T: +1 978-5219700
Email: saleseast@ventec-usa.com

www.ventecclaminates.com