

tec-speed 6.1 - VT-462S(LK)

UL Approval: E214381 Version: 5 /91 /102

Laminate/Prepreg

General Information

- > Very Low Dk & Very Low Loss
- > Excellent Thermal Reliability
- > Lead-free Process Compatible
- > High Tg
- > Ease of Manufacturing

Application

- > High speed Networking equipment
- > IC Tester
- > High Frequency Measuring Instruments and Devices

Availability

- > Core Thickness: 0.002" (0.05mm) to 0.20" (0.5mm), available in sheet or panel form
- > Copper Foil: 1/3oz to 3oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 2116, 2113, 1078, 106, etc
- > Ability of Processing Copper Type: HTE, RTF, VLP & HVLP

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventec laminates.com

tec-speed 6.1 - VT-462S(LK)

UL Approval: E214381 Version: 5 /91 /102

Laminate/Prepreg

Properties Sheet IPC-4101E /91 /102

Properties		Test Method	Units	Specification	Typical Value
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	–	–
	TMA	IPC-TM-650 2.4.24	°C	170 minimum	170
Td		ASTM D3850	°C	340 minimum	400
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288		IPC-TM-650 2.4.24.1	Minute	15 minimum	>30
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum	48
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum	260
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	3.5 maximum	2.8
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	–	11~13
MOT		UL 94	°C	–	130
Electrical Properties					
DK (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	–	–	3.3
	@ 10GHz	IPC-TM-650 2.5.5.13	–	–	3.2
DF (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	–	–	0.0027
	@ 10GHz	IPC-TM-650 2.5.5.13	–	–	0.004
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 [30] minimum	1372 [54]
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 4 (175~250)
Arc Resistance		ASTM D495	Second	60 minimum	124
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	6.0 (1.05)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	4.0 [0.70] minimum	6.0 (1.05)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 [415] minimum	80 [560]
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 [345] minimum	65 [450]
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.10
Flammability		UL-94	Rating	V-1 minimum	V-0

All test data provided are typical values and not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.

308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe

Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA

700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America

T: +1 630-4221627

Email: saleseast@ventec-usa.com

www.ventec laminates.com