

# VT-42(Black)

## Laminate/Prepreg

Version: B4 /21

### General Information

- > Dicy Cured System
- > Standard FR4 (Tg140°C)
- > Black, Light Blocking
- > UV Blocking

### Application

LED, Instrumentation, Watch, etc

### Availability

- > Core Thickness: 0.007" (0.18mm) to 0.040" (1mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, other glass fabric on request

**Note:** For cores 0.005", it is recommended to use the reverse treated copper due to the low profile. The peel strength for RT foil is  $\approx 1-2$ lbs/in (0.35Kg/m) less than standard foil.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

#### CORPORATE HEADQUARTERS

**Ventec Electronics Co. Ltd.**  
308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129  
T: +86 512-68091810  
Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

**Ventec Europe**  
Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK  
T: +44 1926-889822  
Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

**Ventec USA**  
700 Lee St., Elk Grove Village,  
Illinois, IL 60007,  
United States of America  
T: +1 630-4221627  
Email: saleseast@ventec-usa.com

www.ventecclaminates.com

# VT-42(Black)

## Laminate/Prepreg

Version: B4 /21

### Properties Sheet IPC-4101E /21

Properties	Test Method	Units	Specification	Typical Value	
<b>Thermal Properties</b>					
Tg	DSC	IPC-TM-650 2.4.25	°C	110 minimum	140
	TMA	IPC-TM-650 2.4.24	°C	-	-
Td		ASTM D3850	°C	-	305
T260		IPC-TM-650 2.4.24.1	Minute	-	10
T288		IPC-TM-650 2.4.24.1	Minute	-	-
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	150
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	-	50
	After Tg	IPC-TM-650 2.4.24	ppm/°C	-	250
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	-	3.75
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	-	12~14
MOT		UL 94	°C	-	130
<b>Electrical Properties</b>					
DK @ 1GHz		IPC-TM-650 2.5.5.9	-	5.4 maximum	4.5
DF @ 1GHz		IPC-TM-650 2.5.5.9	-	0.035 minimum	0.018
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	-	Grade 4 (100~175)
Arc Resistance		ASTM D495	Second	-	111
<b>Mechanical Properties</b>					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	-	10~12 (1.7~2.0)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	9~12 (1.5~2.0)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	87 (600)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	72 (500)
<b>Physical Properties</b>					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.25
Flammability		UL-94	Rating	V-0 minimum	V-0

Note: All test data provided are typical values and not intended to be specification values.

**CORPORATE HEADQUARTERS**
**Ventec Electronics Co. Ltd.**

 308 TaiShan Rd,  
 New District Suzhou,  
 Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

**EMEA REGIONAL HEADQUARTERS**
**Ventec Europe**

 Unit 1 Trojan Business Centre,  
 Tachbrook Park Estate,  
 Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

**AMERICAS REGIONAL HEADQUARTERS**
**Ventec USA**

 700 Lee St., Elk Grove Village,  
 Illinois, IL 60007,  
 United States of America

T: +1 630-4221627

Email: saleseast@ventec-usa.com

[www.ventecclaminates.com](http://www.ventecclaminates.com)