

VT-447V

UL Approval: E214381 Version: A1 /127 /128 /130 /154

Laminate/Prepreg

General Information

- > Phenolic Cured System
- > Halogen free
- > High Td & High Tg (175 °C)
- > FR15.1 & MOT 150 °C
- > CAF Resistance
- > Low Z-CTE
- > Excellent Thermal Reliability



Application

Mobile Phone, Smart Phone, Automotive, High Power Application, Server, Computer, Communication Equipment, Instrumentation, Electronic Game Machine, VCR, etc.

Availability

- > Core Thickness: 0.002" (0.05mm) to 0.200" (5mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 1500, 2113, 2313, 3313, 2116, 1080, 1086, 1078, 106 & 1067, etc

Note: For cores $\leq 0.005"$, it is recommended to use the reverse treated copper due to the low profile. The peel strength for RT foil is $\approx 1-2\text{lbs/in}$ (0.35Kg/m) less than standard foil.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23 °C (73 °F)	Below 5 °C (41 °F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
700 Lee St., Elk Grove Village,
Illinois, IL 60007,
United States of America
T: +1 630-4221627
Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-447V

UL Approval: E214381 Version: A1 /127 /128 /130 /154

Laminate/Prepreg

IPC-4101E WAM1 /127 /128 /130 /154

Properties		Test Method	Units	Specification	Typical Value
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	–	–
	TMA	IPC-TM-650 2.4.24	°C	170 minimum	175
Td		ASTM D3850	°C	340 minimum	385
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288		IPC-TM-650 2.4.24.1	Minute	15 minimum	>30
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum	40
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum	210
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	3.0 maximum	2.2
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	–	11~13
MOT		UL 746E	°C	–	150
Electrical Properties					
DK @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	–	5.4 maximum	4.35
DF @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	–	0.035 maximum	0.013
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 3 (175-250)
Arc Resistance		ASTM D495	Second	–	195
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	7~9 (1.2~1.6)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	7~9 (1.2~1.6)
Flexural Strength	Warp	IPC-TM-650 2.4.4	KPsi (MPa)	60 (415) minimum	72 (500)
	Fill	IPC-TM-650 2.4.4	KPsi (MPa)	50 (345) minimum	58 (400)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.18
Flammability		UL-94	Rating	V0 minimum	V-0

Note: All test data provided are typical values and are not intended to be specification values.

CORPORATE HEADQUARTERS
Ventec Electronics Co. Ltd.

 308 TaiShan Rd,
 New District Suzhou,
 Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS
Ventec Europe

 Unit 1 Trojan Business Centre,
 Tachbrook Park Estate,
 Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS
Ventec USA

 700 Lee St., Elk Grove Village,
 Illinois, IL 60007,
 United States of America

T: +1 630-4221627

Email: saleseast@ventec-usa.com

www.ventec laminates.com