

tec-speed 8.1 & 8.2H-PK VT-772+(LK) / VT-772+(LK2)

PROCESS GUIDE

UL Approval: E214381 Version: 07/03/2026

Precautions in Handling

Storage Condition & Shelf Life

		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative Humidity	Below 55%	/	/
Shelf Life		3 Months	6 Months	24 Months (airproof)

- Laminate should be stored flat in a cool dry environment. Avoid bending or scratching the laminate surface.
- Prepreg should be stored flat in a cool dry controlled environment 23°C or less and 50% RH or less. Extended storage of prepreg should be at a reduced temperature of 5°C.
- Open bags of prepreg must be resealed. Prepreg should not be exposed to open environments for more than 8 hours total cumulatively under the above conditions or as agreed upon between user and supplier.
- A first-in-first-out inventory system and a method to track material lot numbers through PWB processing and delivery of finished circuits is recommended.

Designing and Inner layer Process

- Please be careful when single ply of 1080, 1086, 1078 or 106 prepreg is designed to the dielectric layer.
- Before feed please baking to remove any absorbed moisture or surface moisture especially for thinner core. Baking at 150°C for 120 minutes is preferred.
- Oxide Alternative is preferred & recommended over the other oxide chemistry for the advanced boards fabrications, especially for lead free and high layer count applications.
- Holding time between brown oxide and press process: best control within 6 hours.

tec-speed 8.1 & 8.2H-PK VT-772+(LK) / VT-772+(LK2)

PROCESS GUIDE

UL Approval: E214381 Version: 07/03/2026

Prepreg Availability

Dk values are for impedance design

VT-772+(LK)

Delivered Thickness (Inches)	Glass Style	Resin Content	Dk					Df				
			@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz	@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz
0.0025	1035	75%	3.02	3.02	3.01	3.00	2.98	0.0015	0.0015	0.0016	0.0017	0.0018
0.0030	1035	78%	2.97	2.97	2.96	2.95	2.93	0.0014	0.0014	0.0015	0.0016	0.0017
0.0030	1078	66%	3.12	3.12	3.11	3.10	3.08	0.0015	0.0015	0.0016	0.0017	0.0018
0.0035	1078	71%	3.07	3.07	3.06	3.05	3.03	0.0015	0.0015	0.0016	0.0017	0.0018
0.0040	1078	75%	3.02	3.02	3.01	3.00	2.98	0.0015	0.0015	0.0016	0.0017	0.0018

VT-772+(LK2)

Delivered Thickness (Inches)	Glass Style	Resin Content	Dk					Df				
			@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz	@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz
0.0025	1035	75%	2.82	2.82	2.81	2.8	2.78	0.0011	0.0011	0.0012	0.0013	0.0014
0.0030	1035	78%	2.77	2.77	2.76	2.75	2.75	0.001	0.001	0.0011	0.0012	0.0013
0.0030	1078	66%	2.92	2.92	2.91	2.9	2.88	0.0011	0.0011	0.0012	0.0013	0.0014
0.0035	1078	71%	2.87	2.87	2.86	2.85	2.83	0.0011	0.0011	0.0012	0.0013	0.0014
0.0040	1078	75%	2.82	2.82	2.81	2.8	2.78	0.0011	0.0011	0.0012	0.0013	0.0014

Remark:

- ① Press thickness test condition---Prepreg lamination size 18"*24", Copper Foil---1oz/1oz, Flow---about 5%;
- ② Make laminated prepreg to micro-section and measure the thickness with microscope; this thickness is used for resistance design calculation.
- ③ The thickness measured with micrometer is 0.2-0.4 mil larger than that measured with micro-section; and mainly used for total thickness design calculation.

tec-speed 8.1 & 8.2H-PK VT-772+(LK) / VT-772+(LK2)

PROCESS GUIDE

UL Approval: E214381 Version: 07/03/2026

Laminates Availability

Dk values are for impedance design

VT-772+(LK)

Delivered Thickness (Inches)	Glass Style	Piles	Resin Content	Dk					Df				
				@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz	@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz
2.0	1035	1ply	68	3.10	3.10	3.09	3.08	3.06	0.0015	0.0015	0.0016	0.0017	0.0018
2.5	1035	1ply	75	3.02	3.02	3.01	3.00	2.98	0.0015	0.0015	0.0016	0.0017	0.0018
3.0	1078	1ply	66	3.12	3.12	3.11	3.10	3.08	0.0015	0.0015	0.0016	0.0017	0.0018
3.5	1078	1ply	71	3.07	3.07	3.06	3.05	3.03	0.0015	0.0015	0.0016	0.0017	0.0018
4.0	1035	2ply	68	3.10	3.10	3.09	3.08	3.06	0.0015	0.0015	0.0016	0.0017	0.0018
5.0	1035	2ply	75	3.02	3.02	3.01	3.00	2.98	0.0015	0.0015	0.0016	0.0017	0.0018
6.0	1078	2ply	66	3.12	3.12	3.11	3.10	3.08	0.0015	0.0015	0.0016	0.0017	0.0018
7.0	1078	2ply	71	3.07	3.07	3.06	3.05	3.03	0.0015	0.0015	0.0016	0.0017	0.0018

VT-772+(LK2)

Delivered Thickness (Inches)	Glass Style	Piles	Resin Content	Dk					Df				
				@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz	@ 1GHz	@ 2GHz	@ 5GHz	@ 10GHz	@ 20GHz
2.0	1035	1ply	68%	2.90	2.9	2.89	2.88	2.86	0.0011	0.0011	0.0012	0.0013	0.0014
2.5	1035	1ply	75%	2.82	2.82	2.81	2.80	2.78	0.0011	0.0011	0.0012	0.0013	0.0014
3.0	1078	1ply	66%	2.92	2.92	2.91	2.90	2.88	0.0011	0.0011	0.0012	0.0013	0.0014
3.5	1078	1ply	71%	2.87	2.87	2.86	2.85	2.83	0.0011	0.0011	0.0012	0.0013	0.0014
4.0	1035	2ply	68%	2.90	2.90	2.89	2.88	2.86	0.0011	0.0011	0.0012	0.0013	0.0014
4.5	1035	2ply	71%	2.87	2.87	2.86	2.85	2.83	0.0011	0.0011	0.0012	0.0013	0.0014
5.0	1035	2ply	75%	2.82	2.82	2.81	2.8	2.78	0.0011	0.0011	0.0012	0.0013	0.0014
6.0	1078	2ply	66%	2.92	2.92	2.91	2.9	2.88	0.0011	0.0011	0.0012	0.0013	0.0014
7.0	1078	2ply	71%	2.87	2.87	2.86	2.85	2.83	0.0011	0.0011	0.0012	0.0013	0.0014


More types could be available upon request

tec-speed 8.1 & 8.2H-PK VT-772+(LK) / VT-772+(LK2) PROCESS GUIDE

UL Approval: E214381 Version: 07/03/2026

Press Condition

1. Heating rate (Rate of Rise) of material [Material Temperature]: Programmable Press: $\geq 3^{\circ}\text{C}/\text{min}$
2. Curing Temperature & Time: $>120\text{min}$ at more than 210°C and peak temperature $>215^{\circ}\text{C}$
3. Full Pressure: $\geq 400\text{psi}$ ($28\text{Kg}/\text{cm}^2$) should be applied full pressure before 100°C
4. Vacuuming should be continued until over 140°C [Material Temperature]
5. Cushion for pressure evenness is needed



Typical Drilling Parameters

- Drilling parameters should be adjusted depending on hole size, layer count, panel thickness, stack count and stack height etc.
- Please adjust drilling parameters after checking qualities of through holes.
- Suggest Drilling parameter as below:

Diameter (mm)	Spindle Speed (krpm)	Feed Rate (IPM)	Retract Rate (IPM)	Hit Counts
0.10mm	200~300	25~38	800	1000
0.20mm	150~200	38~50	800	1000
0.30mm	100~150	38~60	800	1000
0.40mm	80~100	40~50	800	1000

- Smear, resin cracking or nail heading may occur if drilling condition doesn't match material.

tec-speed 8.1 & 8.2H-PK VT-772+(LK) / VT-772+(LK2) PROCESS GUIDE

UL Approval: E214381 Version: 07/03/2026

Laser Drilling

- Brown Oxidation treatment
- Diameter: 80µm
- Pulse width: 1st shot (for copper) 15us, 2nd / 3rd shot (for prepreg) 7us



Desmear Process

- Before using plasma or desmear, a post baking @150°C for 120min is preferred.
- 1 cycle Plasma and 1 cycle desmear is recommended.
- Typical plasma conditions.

Process	Temperature [°C]	Gas Mixture	Power (W)	Duration (min)
Parameter	80-100	10%CF4 , 80% O2, 10% N2	4000	60-80

- Typical Chemical conditions. (Atotech chemical)

Process	Temperature [°C]	Duration (min)
Sewll	60-70	5-10
Permanganate Oxidizer	70-80	10-15

If use other chemical, please consult the chemical supplier for suggested conditions.
Please consult the chemical supplier for suggested conditions.

Packaging and baking recommendation

- It is recommended to bake the board before packaging at 125°C/4~8h to avoid moisture causing a decrease in heat resistance.
- If the PCBs needs to be stored for a long time before use, it is recommended to use aluminum foil vacuum packaging.
- If exceed 3 months after packaging , It is best to bake the PCBs at 125°C/4~6h before assembly before use.