

VT-47

UL Approval: E214381 Version: B3 /97 /98 /99 /101 /126

Laminate/Prepreg

General Information

- > High Tg FR4
- > Phenolic Cure System & Lead Free Compatible
- > Excellent Thermal Reliability
- > CAF Resistance
- > UV Blocking
- > Low Z-CTE

Application

Computer, Communication Equipment, Instrumentation, Precise Apparatus & Instrument, Server, Router, Automotive, Medical, etc

Availability

- > Core Thickness: 0.002" (0.05mm) to 0.200" (5mm), available in sheet or panel form.
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 1500, 2113, 2313, 3313, 2116, 1080, 1086, 1078, 106 & 1067, etc.

Note: For cores $\leq 0.005"$, it is recommended to use the reverse treated copper due to the low profile. The peel strength for RT foil is $\approx 1-2\text{lbs/in}$ (0.35Kg/m) less than Standard foil.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America
T: +1 978-5219700
Email: saleseast@ventec-usa.com

www.ventec laminates.com

VT-47

UL Approval: E214381 Version: B3 /97 /98 /99 /101 /126

Laminate/Prepreg

Properties Sheet IPC-4101D-WAM1 /97 /98 /99 /101 /126

Properties	Test Method	Units	Specification	Typical Value	
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	170 minimum	180
	TMA	IPC-TM-650 2.4.24	°C	–	180
Td		ASTM D3850	°C	–	355
T260		IPC-TM-650 2.4.24.1	Minute	–	>60
T288		IPC-TM-650 2.4.24.1	Minute	–	>30
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	–	45
	After Tg	IPC-TM-650 2.4.24	ppm/°C	–	190
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	–	2.3
MOT		UL 94	°C	–	130
Electrical Properties					
DK @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	–	5.4 maximum	4.27
DF @ 1GHz RC 50%		IPC-TM-650 2.5.5.9	–	0.035 minimum	0.016
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 3 (175~250)
Arc Resistance		IPC-TM-650 2.5.1	Second	60 minimum	147
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	7.5~10 (1.3~1.75)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6 (1.05) minimum	7.5~10 (1.3~1.75)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	72 (500)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	61 (420)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.12
Thermal Conductivity		ISO22007-2	W/M-K	–	0.5
Flammability		UL-94	Rating	V0 minimum	V0

Note: All test data provided are typical values and are not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.

308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe

Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA

21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America

T: +1 978-5219700

Email: saleseast@ventec-usa.com

www.ventec laminates.com